



# MOSO® Bamboo X-treme® 1x4 T&G

MOSO® Bamboo X-treme® 1x4 T&G is a solid, Thermo-Density® board, made from compressed bamboo strips. A special, heat-treatment process at 392°F (200°C) provides MOSO® Bamboo X-treme® the highest durability class possible in the appropriate European standard (see technical characteristics below) and increases the hardness and stability. These floor boards are very suitable for covered outdoor areas. They come pre-primed and thanks to the tongue and groove system the installation is fast and easy. MOSO® Bamboo X-treme® 1x4 T&G can be used for porch flooring, covered ceilings and soffits.



PP: Pre-primed, B: Bevel (also on ends)  
Also available with FSC® certification.

Product Code	Grooved	Finish	Edges	Surface	End-matched	Size	Dimensions (")	Dimensions (mm)
BO-POR-18-96-PP	Yes	PP	B	Smooth	Yes	1 x 4 x 6	3/4 x 3-7/8 x 72	18 x 96 x 1830

## installation summary

(full version available on [www.moso-bamboo.com/x-treme](http://www.moso-bamboo.com/x-treme))

- Install a suitable, fixed, stable and durable joist system.
- The recommended maximum span for 18 mm is 12" on center – but your local building codes may be less.
- Each porch board must be installed flush and tight against the joist system with a fastener insert through the tongue and into the joist.
- Fasteners should be attached at 45 degrees from vertical into the groove on the tongue and into the porch board and joist below. Fasteners should be no larger than 18 gauge flooring cleats.
- The first board and final boards should be face screwed to the joist system using stainless steel screws, predrilled and countersunk.
- Maintenance and cleaning: Routinely remove debris from your porch flooring such as leaves, grass clippings by seeping (with a soft bristle brush) or blowing them off. Power washing of the material is not recommended use only a regular hose and a gentle bristle brush to remove stuck on debris. In order to maintain its original color, you must coat the floor a few months after installation with a penetrating oil finish.

## technical characteristics and certifications

- Density: +/- 71.79 lbs/ft<sup>3</sup>
- Dimensional stability: length: + 0.1 %; width + 0.9% (24 hours in water 68°F)
- Resistance to Indentation - Brinell Hardness: ≥ 65.5 psi (EN 1534)
- Reaction to fire: Class Bfl-s1 (EN 13501-1)
- Flame spread index: Flame spread 25, Smoke developed 45
- Class A (ASTM E84) / CAN/ULC S102 (WUI approved)
- Slip resistance - new material: USRV 55 (Dry), USRV 29 (Wet) (CEN/TS 16165 Annex C) / R 10 (CEN/TS 16165 Annex B - DIN 51130)
- Slip resistance - weathered material: USRV 100 (Dry) (CEN/TS 16165 Annex C) / R 11 (CEN/TS 16165 Annex B - DIN 51130)
- Thermal emittance: 0.81 (ASTM C1371)\*
- Solar Reflectance (SR): 32 (ASTM C1549)\*
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980)\*
- Modulus of Elasticity: 13656 MPa (EN 408, equivalent ASTM D 198)
- Breaking strength: 54.4 MPa (EN 408, equivalent ASTM D 198)
- Biological durability:
  - Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test
  - Class 1 (EN 350 / CEN/TS 15083-1)
- Effectiveness against Blue Stain: Class 0 (EN 152)
- Use Class: Class 4 (EN 335)
- CO<sub>2</sub> neutral: LCA report TU Delft (ISO 14040/44) ([moso.eu/lca](http://moso.eu/lca))
- Environmental Product Declaration - EPD (EN 15804) ([moso.eu/epd](http://moso.eu/epd))
- FSC®: Products available with FSC® certification on request.
- Contribution LEED BD+C - v4: MR 1, MR 2, MR 3 (FSC®) v2009: MR 6, MR 7 (FSC®)
- Contribution BREEAM: MAT 1, MAT 3 (FSC®), MAT 5 (HD)
- Warranty: 25 years

\* ) Tested on 3 years weathered MOSO® Bamboo X-treme®

Class A

WUI

Bfl-s1

E1  
HCHO

CO<sub>2</sub>  
NEUTRAL

EPD  
EN15804

25  
YEARS  
WARRANTY

The mark for responsible forestry  
FSC® C002063  
[www.fsc.org](http://www.fsc.org)  
Only the products defined as such,  
are FSC certified

breeam